FENLITE BACKGROUND 1350

Technical Datasheet





PRODUCT APPLICATIONS

| BLOCK WIDTH / Compressive Strength | CAVITY WALLS External leaf Below DPC | CAVITY WALLS External leaf Above dpc | CAVITY WALLS Inner Leaf Below DPC | CAVITY WALLS Inner Leaf Above DPC | SOLID EXTERNAL Walls Below DPC | SOLID EXTERNAL Walls Above DPC | SEPARATING Walls | INTERNAL Partitions | BEAM & Block floors | SUITABLE For Rendering |
|--|--|--|---|---|--------------------------------------|--------------------------------------|---------------------|------------------------|------------------------|---------------------------|
| 100mm / 3.6N | × | ✓ 4 | x | ✓ | x | ✓ 4 | ✓ 5 | ✓ | × | ~ |
| 100mm / 7.3N | 1, 2, 3 | ✓ 4 | ✓ 1, 2 | ✓ | 1, 2, 3 | ✓ 4 | ✓ 5 | ✓ | ✓ 6 | ~ |
| 100mm / 10.4N | 1, 2, 3 | ✓ 4 | ✓ 1, 2 | ✓ | 1, 2, 3 | ✓ 4 | ✓ 5 | ✓ | ✓ 6 | ~ |
| 140mm / 7.3N 🗥 | 1, 2, 3 | ✓ 4 | ✓ 1, 2 | ✓ | 1, 2, 3 | ✓ 4 | ✓ 5 | ✓ | × | ~ |
| 140mm / 10.4N*🛆 | 1, 2, 3 | ✓ 4 | ✓ 1, 2 | ✓ | 1, 2, 3 | ✓ 4 | ✓ 5 | ✓ | × | ~ |

Notes:

- Products suitability in this application is subject to the block achieving the sites soil / groundwater DS classification requirements.
- Blocks must have either a minimum compressive strength of 7.3N or a minimum density of 1500 kg/m³ when used below dpc level.
- 3. Blocks in the external leaf from dpc level to 150mm below ground level must not be left exposed, suitable products such as clay bricks of Class B Engineering properties or "F2" durability in accordance with BS EN 771-1 should be specified in this zone, alternatively blocks may be covered with a suitable protective finish.
- For all external leaf applications, the block requires a suitable impervious coating or finish applied, blocks must not be left exposed when used on the external leaf.
- Product suitability in this application is subject to the block achieving the walls specification requirements for sound reduction or those specification criteria set in the Robust Detail selected.
- For beam and block infill applications, aggregate blocks must have a minimum compressive strength of 7.3 N/mm².

- The Paint Grade block is a premium product which is manufactured to produce a close face texture and technically can be used in this situation. Commercially, suitable background blocks may be a more suitable specification in this situation.
- 8. Estimated figure only, tested values are generally 1 3 dB lower.

Products should be designed and constructed in accordance with all relevant Legislation, Building Regulations, European & British Standards, Acts, Codes of Practice and manufacturers recommendations.

Please refer to Building Regulations, Approved Document A and the Project Structural Engineer for minimum wall thickness, block compressive strength and characteristic strength requirements - specification varies subject to numerous factors which include loading, block orientation, restraint, wall height and length.

Block weights based on gross density plus 10% @ 5% (Evalast products) or 15% (Fenlite products) moisture content (typical received), moisture equilibrium approximately 3% (protected) and 5% (exposed).

NPD No performance declaration - please contact Forterra for further information. *Manufactured to special order only. CAUTION HEAVY ITEMS >20kg.

FENLITE BACKGROUND 1350

Technical Datasheet

V2 04-24

PRODUCT TECHNICAL PROPERTIES

Blocks are manufactured to BS EN 771-3.

| Material Properties | | | | | |
|--|---|-------------------|--|--|--|
| Thickness (mm): | 100 | 140 🛆 | | | |
| Face Sizes – L x H (mm): | 440 x 215 | | | | |
| Dimension Tolerance Classification: | D1 | | | | |
| Dimension Tolerance – Length: | (+3mm -5mm) | | | | |
| Dimension Tolerance – Height: | (+3mm -5mm) | | | | |
| Dimension Tolerance – Width: | (+3mm -5mm) | | | | |
| Unit Weight, Gross Density + 10% @ 15% Moisture (kg): | 16.2 | 22.6 | | | |
| Configuration: | Group 1 (Solid) | | | | |
| Category: | 11 | | | | |
| Mean Compressive Strength (N/mm ²): | 3.6, 7.3, 10.4 | 7.3, 10.4 | | | |
| Gross Dry Density (Kg/m³): | 1350 | | | | |
| Thermal Conductivity - λ10, dry unit, S1 (W/m.K): | 0.4 | | | | |
| Design Thermal Conductivity - Protected (3%) (W/m.K): | 0.4 | 5 | | | |
| Design Thermal Conductivity - Exposed (5%) (W/m.K): | 0.4 | 9 | | | |
| Design Thermal Conductivity - Below Dpc Level (W/m.K): | NPD | | | | |
| Thermal Resistance - Protected (3%) (m ² .K/W): | 0.222 | 0.311 | | | |
| Thermal Resistance - Exposed (5%) (m².K/W): | 0.204 | 0.286 | | | |
| Sound Reduction – Un-finished (RW dB): | 44.2 ⁸ | 47.4 ⁸ | | | |
| Fire Resistance (Hours) (NA to BS EN 1996-1-2) – | | | | | |
| Non-load Bearing Single Leaf walls (Criteria El): | 4 | | | | |
| | | | | | |
| Fire Resistance (Hours) (NA to BS EN 1996-1-2) – | 0 | | | | |
| Load Bearing Single Leaf walls (Criteria REI) \leq 1.0: Load Bearing Single Leaf walls (Criteria REI) \leq 0.6: | 2 3 | 3 4 | | | |
| | | | | | |
| Reaction to Fire (BS EN 13501): | A1 | | | | |
| Durability Against Freeze / Thaw: | Not to be left exposed | | | | |
| Water Vapor Permeability: | 5/15 | | | | |
| Dimensional Stability - Moisture Movement (mm/m): | < 1.5 mm/m | | | | |
| Vapour Resistivity (MN.s/g.m): | 75 | | | | |
| Soil or Groundwater DS Classification: | DS1 ² | | | | |
| Shear Bond Strength (N/mm ²): | 0.15 | | | | |
| Movement Joint Detail | Vertical movement joints at 6m centres and not more than half that spacing from a corner | | | | |

Notes

△ CAUTION HEAVY ITEMS >20kg Warning.

Forterra Design & Technical Services

Tel: 0330 123 1018 | Email: asktechnical@forterra.co.uk Atherstone Road, Measham, Derbyshire DE12 7EL

Page 2 of 2

